

INTENDED USES:

A hard, flat enamel undercoat for use as an interior/exterior intermediate coat in a three-coat enamel system. Also for use as a first coat over existing gloss finishes when repainting. Provides excellent sanding properties.

PRODUCT DESCRIPTION:

A highly pigmented, modified alkyd.

TECHNICAL INFORMATION:

Finish:	Flat
Standard Colours:	White
Tint Range:	Light, medium & dark colours
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	39-52 m ² /3.7L (420-560 ft ² /3.7L)
Typical Volume Solids:	52%
Typical Specific Gravity:	1.5
Flash point:	44°C (111°F)
Application Thinner:	Low Odour Thinner
Clean-up Thinner:	Low Odour Thinner or Regular Mineral Spirits

SURFACE PREPARATION:

Surface must be clean, dry and free from dust, grease, mildew or remove any loose peeling paint and repair with a patching compound.

Prime as required below.

New Drywall: Seal with 51-087 latex super seal.

New Wood: Prime with 02-230 alkyd primer/sealer

Previously Painted Surfaces: Although no sanding is required on glossy surfaces, it will improve the adhesion and application properties.

Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2-4 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum

PRODUCT HAZARDS _SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

*Brushing recommended for new wood because the brushing action will promote penetration of the product into the wood.



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

Complies with the requirements of MPI #46.