

## Fish Hold Enamel

### INTENDED USES:

A durable enamel intended for painting the holds on fishing vessels to prevent contamination of the catch. Designed for coating wood and suitably primed metal and Fibreglas fish holds. CAN BE APPLIED TO SURFACES MOIST DUE TO CONDENSATION such as in dairies, food processing plants, etc.

### PRODUCT DESCRIPTION:

A synthetic resin pigmented with specially selected pigments and containing emulsifying agents for absorbing minor amounts of water into the film.

---

### TECHNICAL INFORMATION:

**Finish:**

Full

**Standard Colours:**

White

**Tint Range:**

Light Millennium colours

**Recommended # of coats:**

1-2 at recommended coverage

**Theoretical Coverage:**

33-43 m<sup>2</sup>/3.7L (350-460 ft<sup>2</sup>/3.7L)

**Typical Volume Solids:**

44%

**Typical Specific Gravity:**

1.1

**Flash point:**

45°C (113°F)

**Application Thinner:**

Mineral Spirits

**Clean-up Thinner:**

Mineral Spirits

---

### SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Prime as required below. Surface repairs should be spot primed.

New Wood: Prime with 32-002 Exterior Oil Primer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

### APPLICATION:

Brush, Roller, Air Spray or Airless Spray. On damp surfaces use a brush only - the mechanical action of brushing will pick up the residual film of moisture.

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2-4 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum*.

### PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

### ADDITIONAL DATA:

Not suitable for fish ponds or any areas where "live" fish are housed.

\*Drying time will vary with the amount of moisture present. Canadian Food Inspection Agency: Accepted construction materials for coating walls & ceiling, and potable water contact.

### Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the