

28-030

General Paint.

Tradesman Interior Pearl Latex

INTENDED USES:

An interior pearl latex finish designed to provide a durable finish for hallways, living and dining rooms, etc., were a flat finish would be difficult to maintain. Not suitable for areas where excess moisture occurs (e.g. bathrooms). Designed for new construction or renovation.

PRODUCT DESCRIPTION:

A professional quality latex paint formulated with titanium dioxide and inert pigments.

TECHNICAL INFORMATION:

Finish:

Pearl

Standard Colours:

White

Tint Range:

Light Millennium colours

Recommended # of coats:

1-2 at recommended coverage

Theoretical Coverage:

27-36 m²/3.7L (290-390 ft²/3.7L)

Typical Volume Solids:

33%

Typical Specific Gravity:

1.3

Flash point:

Not Applicable

Application Thinner:

Water, if required for spraying.

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required below. Surface repairs should be spot primed.

New Drywall: Seal with 28-080 Latex Drywall Sealer.

New Wood: Prime with 29-080 Tradesman Alkyd Primer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 51-050 Latex Plastic Primer to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15 to 30 minutes
To Handle:	2-4 hours
To Overcoat:	4 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

Complies with the requirements of MPI #52.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.