

46-087

General Paint.

Spantex Deck Coating - Acrylic Latex Texture Tread

INTENDED USES:

A heavy bodied pure acrylic latex coating for wood and plywood decks, balconies, concrete patios, porches, stairs, floors, etc. The textured finish contains a rubber aggregate to provide a non-slip, durable, seamless textured surface. The high build of this product combined with its good flexibility and excellent weather resistance makes it an ideal choice for fully exposed decks.

PRODUCT DESCRIPTION:

A durable and flexible acrylic latex pigmented with light-fast pigments. Contains ground rubber particles to provide a non-slip texture finish.

TECHNICAL INFORMATION:

Finish:

Flat

Standard Colours:

Grey 46-087

Tint Range:

N/A

Recommended # of coats:

1-2 at recommended coverage

Theoretical Coverage:

8-10 m²/3.5L (90-110 ft²/3.5L)

Typical Volume Solids:

52%

Note: It is important to use the quantity recommended to achieve the build required for good durability.

Typical Specific Gravity:

1.3

Flash point:

Not Applicable

Application Thinner:

DO NOT THIN.

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surface must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint. Glossy surfaces must be thoroughly sanded. All seams and cant strips must be secured with polyester tape embedded in SPANTEX LATEX TOPCOAT.

Concrete Floor: Concrete, including repairs, must be cured (minimum 28 days) before application. Wash weathered concrete using a suitable detergent and pressure washer (minimum of a pressure tip on a garden hose). Acid etch new, smooth concrete with a pH that is not within the 6.8 to 8.0 range and rinse thoroughly until the pH is within the given range. Allow a minimum of three days to dry after washing, rain or dew.

Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Roller and brush for cut-in.

Airless Tips: N/A

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15-60 minutes
To Handle:	1-2 hours
To Overcoat:	4 hours (takes 28 days to fully cure)

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

Must be topcoated with 46-line Spantex Topcoat for coating performance and colour uniformity. For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. Allow 24 hours for light foot traffic. Do not replace heavy furniture or subject to

heavy wear for at least 7 days. Concrete Floor: Allow surface to dry completely and ensure that there is no moisture as a result of hydrostatic pressure. To determine if moisture is present as a result of hydrostatic pressure of ground moisture, tape 2 ft² pieces of polythene film on various locations and leave overnight. If there is any moisture visible on the plastic sheets, then there is ground moisture and the substrate is unsuitable for coating. For further information, refer to the General Paint "How-to-Apply DECK COATINGS - Hypalon or Acrylic Latex". Only available in cloud grey Texture Tread, but the 46-Line Spantex top coat may be used for other colours.

Complies with the requirements of MPI #127.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.