

# 47-LINE



## Farmcare Gloss Alkyd

### INTENDED USES:

Exterior high gloss finish for use on primed or previously painted wood, metal, concrete and masonry. Provides a tough, weather resistant coating on wall surfaces, doors, sash and trim.

### PRODUCT DESCRIPTION:

An alkyd vehicle pigmented with light fast pigments.

---

### TECHNICAL INFORMATION:

#### Finish:

Gloss

#### Tint Range:

N/A

#### Theoretical Coverage:

25-33 m<sup>2</sup>/3.7L (260-350 ft<sup>2</sup>/3.7L)

#### Typical Specific Gravity:

1.1

#### Application Thinner:

Not normally required. Use Mineral Spirits if required for spraying.

#### Standard Colours:

White (47-010), Brilliant Red (47-026), and Ranch Red (47-030)

#### Recommended # of coats:

1-2 at recommended coverage

#### Typical Volume Solids:

32%

#### Flash point:

45°C (113°F)

#### Clean-up Thinner:

Mineral Spirits

---

### SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Prime as required below. Surface repairs should be spot primed.

New Wood: Prime with 32-002 Exterior Oil Primer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

### APPLICATION:

Brush, Roller, Air Spray or Airless Spray.

Airless Tips: .013"- .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	4-6 hours
To Handle:	8-12 hours
To Overcoat:	24 hours minimum

### PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data sheet for complete Health & Safety information.

### ADDITIONAL DATA:

If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 10-25°C and 40-60% respectively, at the time of application and for four hours afterward.

### Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the