

# 47-200



## Agricoat Waterborne Gloss Enamel

### INTENDED USES:

A quick drying, gloss acrylic finish with exceptional adhesion to new surfaces and previously painted latex and alkyd finishes. Ideal for the interior and exterior of hog, dairy and poultry facilities where a tough, easy-to-clean, non-yellowing gloss finish is required. Unlike traditional alkyd paints, this waterbourne coating can be recoated in just four hours and is suitable for use in pregnant mare facilities.

### PRODUCT DESCRIPTION:

A pigmented 100% acrylic latex containing a fungicidal agent to inhibit mildew growth on the surface of the coating.

---

### TECHNICAL INFORMATION:

#### Finish:

Gloss

#### Standard Colours:

White

#### Tint Range:

Light Millennium colours

#### Recommended # of coats:

1-2 at recommended coverage

#### Theoretical Coverage:

26-34 m<sup>2</sup>/3.7L (275-370 ft<sup>2</sup>/3.7L)

#### Typical Volume Solids:

35%

#### Typical Specific Gravity:

1.2

#### Flash point:

Not Applicable

#### Application Thinner:

Not normally required. Up to 10% water may be used, if required, for spraying.

#### Clean-up Thinner:

Water

---

### SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Prime as required below. Surface repairs should be spot primed.

New Wood: Prime with 32-002 Exterior Oil Primer or 70-002 Latex Wood Primer.

New Drywall: Prime with 51-087 Latex Super Seal.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

Concrete and Masonry: Allow to age 28 days. No primer required. 70-224 Latex Block Filler can be used to reduce texture on rough surfaces.

Metal and Other Surfaces: Consult your GP Paint Pro.

### APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15 to 30 minutes
To Handle:	2 hours
To Overcoat:	4 hours minimum

### PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

### ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to

painting. The coating should be allowed to dry for a minimum of 48 hours before subjecting to condensation and cured for 30 days before washing.

### **Legal Details**

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.