

# 50-LINE

# General Paint.

## Breeze Interior Semi-Gloss Latex

### INTENDED USES:

A quick-drying semi-gloss finish suitable for interior use on plaster, drywall, concrete and suitably primed surfaces. Provides a tough finish in hallways & living areas where a flat finish would be difficult to maintain. Not suitable where excess moisture occurs, i.e. bathrooms. Has spatter free application properties.

### PRODUCT DESCRIPTION:

A high quality latex vehicle pigmented with inert pigments.

### TECHNICAL INFORMATION:

#### Finish:

Semi-Gloss

#### Tint Range:

Full range of Millennium colours

#### Theoretical Coverage:

25-33 m<sup>2</sup>/3.7L (270-360 ft<sup>2</sup>/3.7L)

#### Typical Specific Gravity:

1.2

#### Application Thinner:

Not normally required. Up to 10% water if needed for spraying.

#### Standard Colours:

White

#### Recommended # of coats:

1-2 at recommended coverage

#### Typical Volume Solids:

33%

#### Flash point:

Not Applicable

#### Clean-up Thinner:

Water

### SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required below. Surface repairs should be spot primed.

New Drywall: Seal with 51-087 Latex Super Seal.

New Wood: Prime with 02-230 Alkyd Primer Sealer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 51-050 Latex Plastic Primer to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

### APPLICATION:

Brush, Roller, Air Spray or Airless Spray.

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15-60 minutes
To Handle:	1-2 hours
To Overcoat:	4 hours (takes 28 days to fully cure)

### PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

### ADDITIONAL DATA:

If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. Consult your GP Paint Pro.

Complies with the requirements of MPI #54.

### Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.