

# 51-260



## Roc-Ceil Spray-On Latex Texture Undercoat

### INTENDED USES:

A high opacity, fast drying undercoat, specifically designed for use on new drywall and properly prepared concrete which is applied prior to the application of textured ceiling finishes. Helps provide a uniform finish and hiding to the textured topcoat. Not suitable for use as a sealer or undercoat for any other application.

### PRODUCT DESCRIPTION:

A highly pigmented latex undercoat.

---

### TECHNICAL INFORMATION:

#### Finish:

Flat

#### Tint Range:

N/A

#### Theoretical Coverage:

25-34 m<sup>2</sup>/3.7L (270-360 ft<sup>2</sup>/3.7L)

#### Typical Specific Gravity:

1.5

#### Application Thinner:

Not Recommended

#### Standard Colours:

White

#### Recommended # of coats:

1-2 at recommended coverage

#### Typical Volume Solids:

33%

#### Flash point:

Not Applicable

#### Clean-up Thinner:

Water

---

### SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew, release agents, wax and loose material. Drywall joints and patched areas must be dry and free from sanding dust. Concrete should be fully cured (a minimum of 28 days) prior to application. Concrete must be free of curing compounds and release agents.

### APPLICATION:

Airless Spray

Airless Tips: .015" - .021"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15-30 minutes
To Handle:	1-2 hours
To Overcoat:	3 hours minimum

### PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

### ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. Designed for new drywall and concrete only. Not recommended on previously painted surfaces.

### Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.