

53-LINE



Black Label Hi-Hide Low Sheen Latex

INTENDED USES:

A quick drying hi-hide interior low sheen latex finish designed for the needs of the professional Painter. Excellent hide and touch-up properties. Not suitable for areas where excess moisture occurs (e.g. bathrooms and kitchens). Designed for new construction or renovation.

PRODUCT DESCRIPTION:

A high quality latex vehicle formulated with titanium dioxide and inert pigments.

TECHNICAL INFORMATION:

Finish:

Low sheen

Tint Range:

Light colours, Latex Colour Book

Theoretical Coverage:

22-30 m²/3.7L (240-320 ft²/3.7L)

Typical Specific Gravity:

1.3

Application Thinner:

Water, if required for spraying.

Standard Colours:

White

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

30%

Flash point:

Not Applicable

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required below. Surface repairs should be spot primed.

New Drywall: Seal with 51-010 Hi-hide Sealer.

New Wood: Prime with 02-230 Alkyd Primer Sealer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 51-050 Latex Plastic Primer to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15 to 30 minutes
To Handle:	2-4 hours
To Overcoat:	4 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.