

59-LINE

General Paint.

Z-coat Flat

INTENDED USES:

A fast drying, high performance flat latex finish for interior applications in areas where a durable, washable finish is required. The low odour and VOC levels makes this product ideal for sensitive areas where odours are undesirable for example in hospitals, schools and other occupied buildings.

PRODUCT DESCRIPTION:

A high performance acrylic paint formulated to near zero VOC levels (~5 g/l). The result is a extremely low odour and more environmentally friendly product.

TECHNICAL INFORMATION:

Finish:

Flat

Tint Range:

Full range of Millennium colours

Theoretical Coverage:

30-40 m²/3.7L (320-430 ft²/3.7L)

Typical Specific Gravity:

1.5

Application Thinner:

Not normally required. Up to 10% water may be used, if required, for spraying.

Standard Colours:

White

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

40%

Flash point:

Not Applicable

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required below. Surface repairs should be spot primed.

New Drywall: Seal with 59-001 Z Coat Drywall Sealer.

New Wood: Prime with 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 51-050 Latex Plastic Primer to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15 to 30 minutes
To Handle:	1 hour
To Overcoat:	2-4 hours

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. A curing period of 7-10 days is required before the optimum properties are achieved.

*Colorant, that can be added to the product will increase the VOC levels and may add some odour to the paint. Complies with the

MPI requirements for MPI category # 143 - Institutional Low Odour/VOC, Interior Latex, Flat.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.