

70-020



Stucco Coat

INTENDED USES:

A flat finish for exterior or interior concrete, masonry, cement/fiber board, stucco, and brick. Provides an acid and alkali resistant film that allows the substrate to 'breathe'. May also be used as a concrete and masonry sealer prior to the application of oil based finishes.

PRODUCT DESCRIPTION:

A latex pigmented with titanium dioxide and other chemical resistant pigments.

TECHNICAL INFORMATION:

Finish:

Flat

Tint Range:

Light ColorLife colours

Theoretical Coverage:

23-31 m²/3.7L (250-340 ft²/3.7L)

Typical Specific Gravity:

1.3

Application Thinner:

Water, if required for spraying.

Standard Colours:

White

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

31%

Flash point:

Not Applicable

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress.

Prime as required below. Surface repairs should be spot primed.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

Concrete and Masonry: Allow to age 28 days. No primer required. 70-224 Latex Block Filler can be used to reduce texture on rough surfaces.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .019"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15 to 30 minutes
To Handle:	2 hours
To Overcoat:	4 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward.

If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting.

If tilt-up construction has been used, curing compounds & release agents must be removed before coating.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.