

72-LINE



Woodcraft Solid Colour Latex Stain

INTENDED USES:

A quick drying, densely pigmented latex stain for exterior smooth or rough siding, shakes, shingles and fencing. Ideally suited for new or previously stained wood, which can be used for low temperature application.

PRODUCT DESCRIPTION:

Light fast pigments dispersed in a modified acrylic latex.

TECHNICAL INFORMATION:

Finish:

Flat

Tint Range:

140 standard stain colours

Theoretical Coverage:

20-27 m²/3.7L (220-290 ft²/3.7L)

Typical Specific Gravity:

1.2

Application Thinner:

Not normally required. Up to 10% water if needed for spraying.

Standard Colours:

White (72-010)

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

27%

Flash point:

Not Applicable

Clean-up Thinner:

Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Surface repairs should be spot primed.

New Wood: Primer not required, but when using white or a light colour, prime with 32-002 Exterior Oil Primer or 70-002 Latex Wood Primer to prevent tannin staining.

APPLICATION:

Brush (preferred*), Roller, Air Spray or Airless Spray.

Airless Tips: .011" - .015"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15-60 minutes
To Handle:	1-2 hours
To Overcoat:	4 hours (takes 28 days to fully cure)

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

Complies with the requirements of MPI #16.

*Brushing is preferred because the stain is worked into the surface and a more uniform distribution is achieved. To avoid lap marks, keep a "wet" edge by stopping only at natural breaks. May be applied to slightly damp (not wet) surfaces. Do not use on roofs or decks. Not recommended over glossy surfaces or previously painted surfaces.

If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting.

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and

40-60% respectively, at the time of application and for four hours afterward.

Drying time will vary depending on temperature, air circulation and humidity. The surface and air temperature must remain above 2°C while the humidity remains below 70%. If painting in cold conditions the temperature must not fall below freezing for at least 8 hours. Recoat time at lower temperatures requires a minimum of 24 hours when temperatures are below 10°C. Do not apply if snow, rain, frost, fog or damp conditions are expected within 24 hours after application.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.