

75-102



Polyurethane Single Component

INTENDED USES:

A clear gloss varnish-type finish that provides greater hardness and abrasion resistance than conventional varnishes. Used extensively as a high quality floor finish and on paneling, cabinets, furniture and millwork. (High solids content provides excellent hold-out).

PRODUCT DESCRIPTION:

Drying oil modified polyurethane resin.

TECHNICAL INFORMATION:

Finish:

Full

Tint Range:

N/A

Theoretical Coverage:

32-42 m²/3.7L (340-450 ft²/3.7L)

Typical Specific Gravity:

0.9

Application Thinner:

Mineral Spirits

Standard Colours:

Clear

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

43%

Flash point:

42°C (108°F)

Clean-up Thinner:

Mineral Spirits

SURFACE PREPARATION:

Wood must be clean, dry and free from dust, grease, mildew and wax. Thin first coat 10-15% for improved adhesion.

APPLICATION:

Brush, Air Spray, Airless Spray, or Applicator pad

Airless Tips: .009" - .013"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	3-4 hours
To Handle:	6 hours
To Overcoat:	16 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

Flammable: This product is flammable. Do not smoke when using this product and ensure that there are no ignition sources (i.e. pilot lights, gas appliances, power tools and other electrical devices) in the area of use.

Do not use in confined areas without the proper safety precautions/equipment.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 10-25°C and 40-60% respectively, at the time of application and for four hours afterward.

For application on floors, best results are obtained with thin coats well brushed out.

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.