

34-030

General Paint.

Monamel Waterborne Alkyd

INTENDED USES:

An Interior / Exterior architectural eggshell enamel finish for properly prepared plaster, concrete, masonry, drywall, wood, metal and steel. When compared to acrylic products, Monamel is smoother and more washable making it ideal for doors, trims and other surfaces requiring frequent washing.

PRODUCT DESCRIPTION:

Advanced Alkyd technology with oil linking to water pigmented with durable light-fast pigments.

TECHNICAL INFORMATION:

Finish:

Eggshell

Tint Range:

Full Range of Colours

Theoretical Coverage:

31-41 m²/3.7L (330-440 ft²/3.7L)

Typical Specific Gravity:

1.4

Application Thinner:

Not normally required. Up to 5% water may be used, if required, for spraying.

Standard Colours:

White

Recommended # of coats:

1-2 at recommended coverage

Typical Volume Solids:

41%

Flash point:

Not Applicable

Clean-up Thinner:

Water (A final rinse with Mineral Spirits may be required)

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Prime as required below. Surface repairs should be spot primed.

New Wood: Prime with 60-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 60-050 Latex Plastic Primer to provide good adhesion. Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	30 to 60 minutes
To Handle:	3-4 hours
To Overcoat:	24 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. A curing period of 7-10 days is required before the optimum properties are achieved. Consult your GP Paint Pro.

NOT RECOMMENDED FOR HORIZONTAL SURFACES

Legal Details

The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied, is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.