

**INTENDED USES:**

An oil rich primer for exterior use on new wood, plywood or medium density overlaid plywood. Should be used on new cedar, red wood or spruce siding under light colour solid colour stains to prevent bleeding of tannin and other soluble stains.

**PRODUCT DESCRIPTION:**

Fortified oil vehicle pigmented to provide opacity, holdout, adhesion and a suitable base for subsequent coatings. A special pigment minimizes tannin and other staining, e.g. tannin. Contains a fungicidal agent.

**TECHNICAL INFORMATION:**

<b>Finish:</b>	Flat
<b>Standard Colours:</b>	White
<b>Tint Range:</b>	Light Millennium colours
<b>Recommended # of coats:</b>	1-2 at recommended coverage
<b>Theoretical Coverage:</b>	48-64 m <sup>2</sup> /3.7L (520-690 ft <sup>2</sup> /3.7L)
<b>Typical Volume Solids:</b>	64%
<b>Typical Specific Gravity:</b>	1.5
<b>Flash point:</b>	54°C (129°F)
<b>Application Thinner:</b>	Mineral Spirits
<b>Clean-up Thinner:</b>	Mineral Spirits

**SURFACE PREPARATION:**

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress.  
New Wood Only:  
Not designed for previously painted or varnished wood.

**APPLICATION:**

Brush (preferred\*), Roller or Spray  
Airless Tips: .013" - .017"  
Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	8-10 hours
To Handle:	18 hours
To Overcoat:	24 hours minimum

**PRODUCT HAZARDS SAFETY INFORMATION:**

See Material Safety Data Sheet for complete Health and Safety information.

**ADDITIONAL DATA:**

Two coats recommended for exterior plywood.

\*Brushing recommended for new wood because the brushing action will promote penetration of the product into the wood. For spot priming or previously painted surfaces 32-001 Alkyd Primer is the recommended product.

Drying problems may be encountered with 01-002 if it is applied to any damp or low porosity surface.

Product  
**01-002**

**Woodcraft Oil  
Primer**



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.