

## INTENDED USES:

A densely pigmented stain for exterior smooth or rough siding, shakes, shingles and fencing. Formulated to give a uniform colour to the wood without concealing the natural texture of the wood.

The lower build of a stain compared to a paint provides better moisture vapour permeability and reduces the tendency of the film to blister and crack with aging. Not intended for roofs or decks.

## PRODUCT DESCRIPTION:

Light fast pigments dispersed in a synthetic resin and fortified oil vehicle. Contains a strong fungicide to inhibit mildew growth on the surface of the coating.

## TECHNICAL INFORMATION:

<b>Finish:</b>	Flat
<b>Standard Colours:</b>	White (01-010)
<b>Tint Range:</b>	140 standard Woodcraft colours
<b>Recommended # of coats:</b>	1-2 at recommended coverage
<b>Theoretical Coverage:</b>	32-43 m <sup>2</sup> /3.7L (350-460 ft <sup>2</sup> /3.7L)
<b>Typical Volume Solids:</b>	45%
<b>Typical Specific Gravity:</b>	1.3
<b>Flash point:</b>	52°C (126°F)
<b>Application Thinner:</b>	Not normally required. Up to 10% Mineral Spirits for spraying.
<b>Clean-up Thinner:</b>	Mineral Spirits

## SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax.

Remove any loose and peeling stain.

Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress.

Prime as required below.

New Wood: No primer required but 01-002 recommended for white or off-white colours to control tannin staining.

## APPLICATION:

Brush (preferred\*), Roller, Air Spray or Airless Spray.

Airless Tips: .011" - .015"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	8-10 hours
To Handle:	18 hours
To Overcoat:	18 hours minimum

## PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

## ADDITIONAL DATA:



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

\*Brushing is preferred because the stain is worked into the surface and a more uniform distribution is achieved. To avoid lap marks, keep a "wet" edge by stopping only at natural breaks such as window casings, door jambs or the course of siding. For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 10-25°C and 40-60% respectively, at the time of application and for four hours afterward. Do not apply to damp or wet surfaces. Moisture content of wood should be 12% or less. Excessive moisture can result in drying and performance problems (may take months to dry since moisture in the substrate will prevent penetration of the coating).

Do not apply over previously painted surfaces - for use only on new or previously stained wood. Complies with the requirements of MPI #14.