

Product
03-020
White Semi-
Gloss Lacquer

INTENDED USES:

Fast drying lacquer finish for use on interior wood surfaces such as furniture, paneling and millwork.

PRODUCT DESCRIPTION:

A pigmented nitrocellulose lacquer.

TECHNICAL INFORMATION:

Finish:	Semi-Gloss.
Standard Colours:	White
Tint Range:	N/A
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	20-28 m ² /3.7L (220-300 ft ² /3.7L)
Typical Volume Solids:	28%
Typical Specific Gravity:	1.0
Flash point:	6°C (43°F)
Application Thinner:	Up to 10% Lacquer Thinner if required.
Clean-up Thinner:	Lacquer Thinner

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling coating and repair any damaged areas with wood filler. Prepare as required. New Wood: Prime with 03-215 Lacquer Primer Sealer.
Previously Coated Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.
Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Air or Airless Spray (Brush may be used for small areas)

Airless Tips: .009" - .013"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15-30 minutes
To Handle:	30 minutes - 1 hour
To Overcoat:	1 hour minimum

PRODUCT HAZARDS _SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.
Flammable: This product is flammable. Do not smoke when using this product and ensure that there are no ignition sources (i.e. pilot lights, gas appliances, power tools and other electrical devices) in the area of use. Do not use in confined areas without the proper safety precautions/equipment.

ADDITIONAL DATA:

For best results when brushing, apply without too much re-brushing on areas already setting up. Nitrocellulose lacquers can yellow on exposure to strong U.V. light. Do not apply over conventional paints - the strong solvents may attack the existing coating. Complies with the requirements of MPI #124 (03-010) and #123 (03-020)..



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.