

INTENDED USES:

A high gloss enamel for suitable primed interior and exterior surfaces. This product is tough enough for marine and light industrial applications, yet safe enough for household use. Suitable on marine engines up to 121°C (250°F) with some discoloration.

PRODUCT DESCRIPTION:

A highly durable alkyd vehicle combined with highly opaque and light-fast pigments.

TECHNICAL INFORMATION:

Finish:	Gloss
Standard Colours:	White
Tint Range:	Light and medium Millennium colours
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	32-42 m ² /3.7L (340-450 ft ² /3.7L)
Typical Volume Solids:	42%
Typical Specific Gravity:	1.1
Flash point:	45°C (113°F)
Application Thinner:	Not normally required. Up to 10% Mineral Spirits for spraying.
Clean-up Thinner:	Mineral Spirits

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew or wax. Remove all loose rust from steel with a wire brush. Remove any loose and peeling paint and repair with patching compound. Ensure all wood joints and seams are filled with a paintable caulking to prevent moisture ingress. Prime as required below. Surface repairs should be spot primed.

New Wood: Apply Marine Enamel directly to new wood (first coat should be reduced up to 10% with mineral spirits). For an extra smooth finish, prime with 10-062 Marine Undercoat. Prime all plywood or redwood with 32-002 Exterior Oil Primer or 70-002 Latex Wood Primer (this will prevent tannin staining).

Steel: Prime with a Anti-corrosive primer, such as 63-212 Marine Primer.

Fibreglas: Prime with 11-011 Plastic Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .011" - .015"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2-4 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

ADDITIONAL DATA:

Fiberglas areas to be painted should be thoroughly sanded. This sanded surface should then be wiped with a clean, lint-free rag, soaked in a strong solvent such as Toluene. Paint as follows: Prime with 11-011 Plastic Primer; Allow 30 minutes drying minimum; Apply two coats of 10-Line Marine Enamel as directed on the label.