

Product
11-060
Interior
Melamine Low
Lustre Finish

INTENDED USES:

A super smooth and tough low lustre architectural finish specially formulated for interior use on melamine laminated surfaces or previously painted cabinets, doors, furniture, shelving, trim and toys. It can be used for light duty counter tops. Its exceptional flow and levelling characteristics make it an ideal top coat for applications that demand perfect surface uniformity. It is also suitable for use over appropriately primed drywall, millwork, concrete, masonry and metal.

PRODUCT DESCRIPTION:

A high quality urethane reinforced low odour alkyd finish pigmented with titanium dioxide.

TECHNICAL INFORMATION:

Finish:	Eggshell
Standard Colours:	White
Tint Range:	16 Standard Melamine colours
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	41-54 m ² /3.7L (440-580 ft ² /3.7L)
Typical Volume Solids:	55%
Typical Specific Gravity:	1.4
Flash point:	48°C (118°F)
Application Thinner:	Low Odour Thinner, if required for spraying
Clean-up Thinner:	Low Odour Thinner Type 1

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound.

Prime as required below. Surface repairs should be spot primed.

New Wood: Prime with 02-230 Alkyd Primer Sealer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Sanding of glossy surfaces and melamine will improve the application properties and aid in adhesion, no primer is required for these substrates.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2-4 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

All alkyds tend to yellow with age. Where this is a concern, consider using a latex system.



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.