

Product
22-LINE
Premium Alkyd
Interior Semi-
Gloss Enamel

INTENDED USES:

An architectural semi-gloss enamel, for interior use on properly prepared plaster, concrete, masonry, drywall, wood and steel. Widely used for application on walls, ceilings, cupboards, doors and trim.

PRODUCT DESCRIPTION:

Alkyd resin pigmented with durable light-fast pigments.

TECHNICAL INFORMATION:

Finish:	Semi-Gloss
Standard Colours:	White
Tint Range:	Full range of Millennium colours
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	36-48 m ² /3.7L (390-520 ft ² /3.7L)
Typical Volume Solids:	48%
Typical Specific Gravity:	1.3
Flash point:	51°C (124°F)
Application Thinner:	Not normally required. Up to 10% Low Odour Thinner for spraying.
Clean-up Thinner:	Low Odour Thinner

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required. Surface repairs should be spot primed. New Drywall: Seal with 51-087 Latex Super Seal. New Wood: Prime with 02-230 Alkyd Primer Sealer or 70-002 Latex Wood Primer. Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 51-050 Latex Plastic Primer to provide good adhesion. Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .011" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	4-6 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

All alkyds tend to yellow with age. Where yellowing is a concern, consider using a latex system.

Consult your GP Paint Pro. Complies with the requirements of MPI #47. Qualified to CAN/CGSB - 1.57-96.



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.