

INTENDED USES:

A flat finish that is ideal for bedrooms, living rooms, hallways, and ceilings.

PRODUCT DESCRIPTION:

A high opacity pigmented latex designed for professional painters.

TECHNICAL INFORMATION:

Finish:	Flat
Standard Colours:	White
Tint Range:	Light colours from the Prodeck Professional Colour Palette
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	22-30 m ² /3.7L (235-315 ft ² /3.7L)
Typical Volume Solids:	29%
Typical Specific Gravity:	1.4
Flash point:	Not Applicable
Application Thinner:	Not normally required. Up to 10% water may be used, if required, for spraying.
Clean-up Thinner:	Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required below. Surface repairs should be spot primed.

New Drywall: Seal with 26-080 Cover All Latex Sealer.

New Wood: Prime with 09-018 Alkyd Primer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 51-050 Latex Plastic Primer to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .019"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	60 minutes
To Handle:	1-2 hours
To Overcoat:	2 - 4 hours

PRODUCT HAZARDS _SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward. A curing period of 10-28 days is required before the optimum properties are achieved.



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.