

Product
29-020
Tradesman
Interior/Exterior
Semi-Gloss
Alkyd Enamel

INTENDED USES:

An alkyd semi-gloss enamel designed for interior or exterior use on previously painted or primed surfaces. Provides a tough abrasion and weather resistant washable finish for doors, sash, trim, walls and ceilings.

PRODUCT DESCRIPTION:

A professional quality alkyd paint formulated with a durable resin, titanium dioxide and inert pigments.

TECHNICAL INFORMATION:

Finish:	Semi-Gloss
Standard Colours:	White
Tint Range:	Light Millennium colours
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	36-48 m ² /3.7L (380-510 ft ² /3.7L)
Typical Volume Solids:	48%
Typical Specific Gravity:	1.3
Flash point:	44°C (111°F)
Application Thinner:	Not normally required. Up to 10% Mineral Spirits if necessary.
Clean-up Thinner:	Mineral Spirits

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax.
Remove any loose and peeling paint and repair with patching compound.
Prime as required. Surface repairs should be spot primed.
New Drywall: Seal with 51-087 Latex Super Seal.
New Wood: Prime with 29-080 Alkyd Primer Sealer or 70-002 Latex Wood Primer.
Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.
Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray
Airless Tips: .011" - .015"
Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2-4 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

Alkyds tend to yellow with age. Where yellowing is a concern, consider using a latex system.
Complies with the requirements of MPI #174



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.