

INTENDED USES:

A hard, fast drying exterior primer particularly suited for spot priming when repainting, or on new sash, doors and trim. Also suitable as an exterior undercoat for glossy surfaces.

PRODUCT DESCRIPTION:

Alkyd resin containing high opacity pigments. Also contains a fungicidal agent and stain controlling compounds.

TECHNICAL INFORMATION:

Finish:	Flat
Standard Colours:	White
Tint Range:	Light Millennium colours
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	37-49 m ² /3.7L (400-530 ft ² /3.7L)
Typical Volume Solids:	49%
Typical Specific Gravity:	1.3
Flash point:	44°C (111°F)
Application Thinner:	Not normally required. Up to 10% Mineral Spirits if necessary.
Clean-up Thinner:	Mineral Spirits

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

APPLICATION:

Brush (preferred*), Roller or Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	2-4 hours
To Handle:	8-12 hours
To Overcoat:	16 hours minimum

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

May be used on new exterior wood, (other than plywood or siding) where a fast drying primer is required. However, if wood is very dry and porous, 32-002 Exterior Oil Primer can be used. Plywood and siding should be primed with 32-002 Oil Primer or 70-002 Exterior Latex Wood Primer. *Brushing recommended for new wood because the brushing action will promote penetration of the product into the wood. If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 10-25°C and 40-60% respectively, at the time of application and for four hours afterward. Complies with the requirements of MPI #5.

Product
32-001

Exterior Alkyd
Primer



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.