

INTENDED USES:

A quick drying eggshell latex enamel finish for interior use on drywall and other prepared surfaces. Provides a durable finish for architectural service in hallways, living and dining rooms, and other areas where a flat finish would be difficult to maintain. This product has good burnish resistance compared to other eggshell latex's. Not suitable where excess moisture occurs (e.g., bathrooms). Has spatter free application properties.

PRODUCT DESCRIPTION:

A high quality latex vehicle pigmented with inert pigments.

TECHNICAL INFORMATION:

Finish:	Eggshell
Standard Colours:	White
Tint Range:	Full range of Millennium colours
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	30-40 m ² /3.7L (330-440 ft ² /3.7L)
Typical Volume Solids:	41%
Typical Specific Gravity:	1.4
Flash point:	Not Applicable
Application Thinner:	Not normally required. Up to 10% water if needed for spraying.
Clean-up Thinner:	Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Prime as required below. Surface repairs should be spot primed.

New Drywall: Seal with 51-087 Latex Super Seal.

New Wood: Prime with 02-230 Alkyd Primer Sealer or 70-002 Latex Wood Primer.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish or primed with 51-050 Latex Plastic Primer to provide good adhesion.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15-60 minutes
To Handle:	1-2 hours
To Overcoat:	4 hours (takes 28 days to fully cure)

PRODUCT HAZARDS SAFETY INFORMATION:

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

For optimum adhesion and application performance, ensure that the temperature and



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward.
Complies with the requirements of MPI #44.