

Product
58-LINE
HP2000
Interior/Exterior
Hi-Hide
Eggshell
Coating

INTENDED USES:

A fast drying, high performance hi-hide eggshell latex finish for interior and exterior applications in high wear and institutional areas where a flat finish would be difficult to maintain. Suitable for use on new drywall and suitably primed surfaces. The product is suitable for use in areas where moisture and condensation occur or any areas where a durable finish is required.

PRODUCT DESCRIPTION:

A pigmented 100% acrylic latex containing a fungicidal agent to inhibit mildew growth on the surface of the coating.

TECHNICAL INFORMATION:

Finish:	Hi-Hide Eggshell
Standard Colours:	White
Tint Range:	Light and Medium colours, Specialty Latex Colour Book
Recommended # of coats:	1-2 at recommended coverage
Theoretical Coverage:	28-38 m ² /3.7L (300-410 ft ² /3.7L)
Typical Volume Solids:	38%
Typical Specific Gravity:	1.4
Flash point:	Not Applicable
Application Thinner:	Not required for brush or roller application. Use water if required for spraying
Clean-up Thinner:	Water

SURFACE PREPARATION:

Surfaces must be clean, dry and free from dust, grease, mildew and wax. Remove any loose and peeling paint and repair with patching compound. Ensure all joints and seams are filled with a paintable caulking to prevent moisture ingress. Prime as required below. Surface repairs should be spot primed.

New Wood: Prime with 32-002 Exterior Oil Primer or 70-002 Latex Wood Primer.

New Drywall: Prime with 51-087 Latex Super Seal.

Previously Painted Surfaces: Glossy surfaces should be sanded to a dull finish to provide good adhesion.

Concrete and Masonry: Allow to age 28 days. No primer required provided pH is below 9. 70-224 Latex Block Filler can be used to reduce texture on rough surfaces.

Metal and Other Surfaces: Consult your GP Paint Pro.

APPLICATION:

Brush, Roller, Air Spray or Airless Spray

Airless Tips: .013" - .017"

Dry times at 21°C / 70°F and 40%-60% R.H.:

To Touch:	15 to 30 minutes
To Handle:	2 hours
To Overcoat:	4 hours minimum

PRODUCT HAZARDS _SAFETY INFORMATION:



The information contained herein is true and accurate to the best of our knowledge. However, no guarantee or warranty of any kind, express or implied is given with respect to the accuracy or completeness of the said information and data or to the products described herein and we assume no risk or liability for the performance or coverage of or for injury resulting from the handling, use or application of the said information, data or products.

See Material Safety Data Sheet for complete Health and Safety information.

ADDITIONAL DATA:

If mildew is present, the surface should be washed with a chlorine bleach solution (20% household bleach and 1% liquid detergent in warm water) and thoroughly rinsed prior to painting. For optimum adhesion and application performance, ensure that the temperature and relative humidity are between 15-25°C and 40-60% respectively, at the time of application and for four hours afterward.

Canadian Food Inspection Agency: Accepted construction materials for coating walls and ceilings.